



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : G02B 5/02, 5/04</p>	<p>A1</p>	<p>(11) International Publication Number: WO 98/50806 (43) International Publication Date: 12 November 1998 (12.11.98)</p>
<p>(21) International Application Number: PCT/US98/09278 (22) International Filing Date: 6 May 1998 (06.05.98) (30) Priority Data: 08/853,261 9 May 1997 (09.05.97) US (71) Applicant: MINNESOTA MINING AND MANUFACTURING COMPANY [US/US]; 3M Center, P.O. Box 33427, Saint Paul, MN 55133-3427 (US). (72) Inventors: FONG, Bettie, C.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). KRETZMAN, Wade, D.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). KOTCHICK, Keith, M.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). COBB, Sanford, Jr.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). MILLER, Richard, A.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). WILLIAMS, Todd, R.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). TOYOOKA, Kazuhiko; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). (74) Agents: BUCKINGHAM, Stephen, W. et al.; Minnesota Mining and Manufacturing Company, Office of Intellectual Property Counsel, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).</p>		<p>(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).</p> <p>Published With international search report.</p>
<p>(54) Title: BRIGHTNESS ENHANCEMENT ARTICLE</p>		
<p>(57) Abstract</p> <p>A brightness enhancement article that includes: (a) a transparent, flexible substrate; (b) a first major surface having an array of prisms with blunted or rounded peaks characterized by a chord width, cross-sectional pitch width, and radius of curvature in which the chord width is equal to about 20-40 % of the cross-sectional pitch width and the radius of curvature is equal to about 20-50 % of the cross-sectional pitch width; and (c) a second major surface characterized by a plurality of light scattering protrusions. The article has a haze value between about 20-60 % and a transmission value no greater than about 94 % when measured under conditions in which the first surface has a substantially planar topography.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

BRIGHTNESS ENHANCEMENT ARTICLE

Background of the Invention

5 This invention relates to enhancing the on-axis luminance (referred to here as "brightness") of a diffuse lighting device.

 Displays used in devices such as computers feature a material such as a liquid crystal composition and a light source for back-lighting the material. Films disposed between the back light and the display have been used to enhance the
10 brightness of the display by controlling the exit angles of light.

Summary of the Invention

 In general, the invention features a brightness enhancement article that includes: (a) a transparent, flexible substrate; (b) a first major surface that includes an array of linear prisms having blunted or rounded peaks; and (c) a second major
15 surface characterized by a plurality of light scattering protrusions. These protrusions imbue the surface with a matte appearance. The peaks are characterized by a chord width, cross-sectional pitch width, and radius of curvature in which the chord width is equal to about 20-40% of the cross-sectional pitch width and the radius of curvature is equal to about 20-50% of the cross-sectional
20 pitch width. The article has a haze value between about 20-60% and a transmission value no greater than about 94% when measured under conditions in which the first surface has a substantially planar topography.

 The prisms are preferably characterized by a root angle ranging from about 70E to about 110E, more preferably from about 85E to about 95E. Root
25 angles of about 90E are particularly preferred.

 In one preferred embodiment, the second major surface is integral with the substrate (e.g., the protrusions may be in the form of "bumps" made of the substrate material). In another preferred embodiment, the second major surface is defined by a layer that includes a resin provided on the substrate. Where the

second major surface is defined by a separate resin layer, the protrusions may be in the form of particles dispersed in the resin layer, or may be integral with the resin layer itself (e.g., they may be in the form of "bumps" made of the resin).

In one preferred embodiment, the first major surface of the article is
5 integral with the substrate. In such embodiments, the haze and transmission values are measured by applying a material such as an index-matching oil to the first major surface to fill in the "valleys" between the blunted or rounded peaks to render the surface substantially planar.

In another preferred embodiment, the first major surface is defined by a
10 separate layer that includes a resin provided with the above-described prisms. In such embodiments, the haze and transmission values are measured on the article prior to application of this resin layer.

The invention also features a method of enhancing the brightness of a uniform, diffusely-emitting, lighting device that includes placing the above-
15 described brightness enhancement article substantially parallel to a light-emitting surface of the device. The invention further features a uniform, diffusely-emitting, lighting device that includes the above-described brightness enhancement article. Examples of preferred devices include back-lit displays such as back-lit liquid crystal displays.

20 The invention provides a brightness enhancement article having a matte appearance that exhibits good gain, wide viewing angles in both horizontal and vertical planes, soft cut-off, and good abrasion resistance. The matte appearance also helps mask cosmetic imperfections in the article, as well as the device with which the article is used, such as scratches, white spots, and stains which may arise
25 during manufacture or installation.

Other features and advantages of the invention will be apparent from the following description of the preferred embodiments thereof, and from the claims.

Brief Description of the Drawings

FIG. 1 is a cross-sectional view of a multi-layer brightness enhancement article.

FIG. 2 is a cross-sectional view of a monolithic brightness enhancement article.

5

Description of the Preferred Embodiments

The brightness enhancement article features a flexible, transparent base layer and two distinct surfaces, each having a topography designed to act in concert to perform the function of controlling the exit angles of light emitted from a back-lit display where the article is placed substantially parallel to a light-emitting
10 surface of the article. The article may take several forms. Referring to FIG. 1, there is shown a multi-layer brightness enhancement article 10. Article 10 includes a flexible, transparent base layer 12 provided with two separate layers 14, 16 on opposite surfaces of layer 12.

Layer 12 is typically a thin, flexible, polymeric layer made of a material
15 such as polyethylene terephthalate, polymethyl methacrylate, or polycarbonate. The thickness of layer 12 preferably is in the range of about 25 to about 500 microns.

The thickness of layer 14 preferably is in the range of about 1 to about 50 microns. The purpose of layer 14 is to provide a light-diffusing surface. To this
20 end, layer 14 includes a plurality of elements 18 protruding from the surface of layer 14. As shown in FIG. 1, these elements are preferably particles dispersed in a polymeric resin. Examples of suitable particles include silica, alumina, calcium carbonate, and glass and plastic beads. The elements may also be in the form of "bumps" formed from the resin itself or from a different material and deposited on
25 the surface of layer 14; an example of the former is commercially available from A.G. Bayer of Germany under the trade designation "Makrofol."

The size, size distribution, and loading of elements 18 are selected to provide a matte surface with light-diffusing ability, as indicated by the haze and percent transmission of article 10 measured in the absence of layer 16 according to

ASTM D-1003-95 using a Haze-Gard Plus haze meter commercially available from Byk-Gardner of Silver Spring, MD. Preferably, the haze is between about 20-60% and the percent transmission is not greater than about 94%.

Articles featuring a flexible, transparent base layer provided with a
5 layer of resin having a series of particles protruding from its surface are commercially available from Tekra, Inc., New Berlin, WI, under the designation "Marnot™ XL Matte Melinex^R Film" and "Marnot™ XL Matte Lexan^R Film." In particular, the Marnot™ XL Matte Melinex^R Film in grades 55 GU, 35 GU, and 20 GU have been found to be suitable.

10 The thickness of layer 16 preferably is in the range of about 10 to about 75 microns. Layer 16 acts in concert with layer 14 to control the angles at which the light is emitted. Layer 16 is preferably a layer of polymer resin provided with a topography designed to achieve this purpose. Suitable resins include the u.v.-polymerized products of acrylate and/or methacrylate monomers. One particularly
15 preferred resin is the u.v.-polymerized product of a brominated, alkyl-substituted phenyl acrylate or methacrylate (e.g., 4,6-dibromo-2-sec-butyl phenyl acrylate), a methyl styrene monomer, a brominated epoxy diacrylate, 2-phenoxyethyl acrylate, and a hexa-functional aromatic urethane acrylate oligomer, as described in Fong et al., U.S.S.N. _____, entitled "Chemical Composition and Polymers and Polymeric
20 Material Derived Therefrom," filed concurrently herewith, which is assigned to the same assignee as the present application and incorporated herein by reference.

The topography of layer 16 is characterized by an array of linear prisms having blunted or rounded peaks 20 characterized by a chord width 22, cross-sectional pitch width 24, radius of curvature 26, and root angle 28 in which the
25 chord width is equal to about 20-40% of the cross-sectional pitch width and the radius of curvature is equal to about 20-50% of the cross-sectional pitch width. The root angle ranges from about 70-110E, preferably from about 85-95E, with root angles of about 90E being particularly preferred. The placement of the prisms within the array is selected to maximize the desired optical performance. To this

end, for example, the prisms may be arranged to form a plurality of alternating zones having peaks that are spaced at different distances from an arbitrarily selected, common reference plane, as described in Wortman et al., U.S.S.N. _____, filed April 3, 1997 entitled "Light Directing Film Having Variable Height

- 5 Structured Surface and Light Directing Article Constructed Therefrom," which is assigned to the same assignee as the present application and hereby incorporated by reference. To reduce the visibility of moire interference patterns, adjacent groups of peaks may be characterized by different pitch widths, as described in Cobb et al., U.S.S.N. 08/631,073, filed April 12, 1996 entitled "Variable Pitch
- 10 Structured Optical Film," which is assigned to the same assignee as the present application and hereby incorporated by reference.

The topography is preferably imparted onto the surface of the resin according to the processes described in Lu et al., U.S. Patent No. 5,175,030 and Lu, U.S. Patent No. 5,183,597. Specifically, the resin composition is contacted

15 with a master bearing a negative of the desired topography. The resin composition is then cured, e.g., by exposure to ultraviolet radiation, while in contact with the master to impart the desired topography to the resin surface.

The brightness enhancement article may also be in the form of a monolithic article, as shown in FIG. 2. Specifically, brightness enhancement

20 article 30 features a flexible, base layer 32 having a pair of opposed surfaces 34, 36, both of which are integrally formed with base layer 32. Suitable materials for layer 32 are the same as those described above in the case of layer 12 of multi-layer article 10.

Surface 34 features a series of protruding light-diffusing elements 38.

25 These elements may be in the form of "bumps" in the surface made of the same material as layer 32.

Surface 36 features an array of linear prisms having blunted or rounded peaks 40 integrally formed with base layer 32. As in the case of article 10, these peaks are characterized by a chord width 42, cross-sectional pitch width 44, radius

of curvature 46, and root angle 48 in which the chord width is equal to about 20-40% of the cross-sectional pitch width and the radius of curvature is equal to about 20-50% of the cross-sectional pitch width. The root angle ranges from about 70-110E, preferably from about 85-95E, with root angles of about 90E being particularly preferred. As in the case of article 10, the placement of the prisms within the array is selected to maximize the desired optical performance.

The particular method used to create the topography characterizing surface 36 is not critical. One useful molding process is described in Benson et al., U.S.S.N. 08/472,444, filed June 7, 1995, entitled "Ultra-Flexible Retroreflective Cube Corner Composite Sheetings and Methods of Manufacture," which is assigned to the same assignee as the present application and hereby incorporated by reference.

In the case of an article such as article 30, in which the surface bearing the prisms is integral with the base layer, the haze and transmission values are measured by applying a material such as an index-matching oil to the peak-bearing surface to fill in the "valleys" between the blunted or rounded peaks and thereby render the surface substantially planar. Suitable oils have a refractive index substantially equal to the refractive index of the surface. The haze and transmission measurements are then made in accordance with ASTM D-1003-95 using the Haze-Gard Plus haze meter.

The invention will now be described further by way of the following examples. All amounts are given in weight percent unless otherwise noted.

EXAMPLES

Example 1

A photopolymerizable resin was prepared combining a brominated epoxy acrylate (available from UCB-Radcare of Smyrna, GA under the designation "RDX 51027") (52 parts) and 2-phenoxy-ethyl acrylate (available from Henkel Corp., Ambler, PA, under the designation "Photomer 4035") (9 parts), and heating at 100EC to soften the brominated epoxy acrylate, after which the two components

were mixed until fluid. Next, methyl styrene (available from Monomer-Polymer & Dajac Laboratories, Inc., Feasterville, PA as a 70:30 mixture of meta- and para-isomers) (11 parts) and 4,6-dibromo-2-sec-butyl phenyl acrylate (prepared as described in Olson, U.S.S.N. ____, entitled "High Index of Refraction Monomer,"
5 filed concurrently herewith, which is assigned to the same assignee as the present application and hereby incorporated by reference) (25 parts) were blended into the fluid mixture, followed by a hexa-functional aromatic urethane acrylate oligomer (available from UCB-Radcure of Smyrna, GA under the designation "EB-220") (3 parts). A nonionic fluorosurfactant ("FC-430" available from Minnesota Mining &
10 Manufacturing Co., of St. Paul, MN) (0.3) and photoinitiator (2,4,6-trimethylbenzoyl-diphenylphosphine oxide available from BASF of Charlotte, NC under the designation "Lucirin TPO") (3) were then added and mixed together for at least 15 minutes, after which the mixture was heated in an oven at 60-70EC for 30 to 60 minutes.

15 The resulting composition was spread on the smooth side of a Tekra Marnot™ XL Matte Melinex® 55 GU film (available from Tekra Corp., New Berlin, WI) using a knife coater to yield a resin coating having a thickness of 25 microns. The coated film was then placed in contact with a master bearing a micro-fine prismatic pattern. Next, the master and film were heated to 130EF, and
20 then passed under an ultraviolet lamp (300 watts/in²) at a speed of 20-25 ft/min. to cure the resin and simultaneously replicate the prismatic pattern of the master on the resin surface. Following cure, the coated film was separated from the master to yield a product having a surface characterized as follows:

	chord width	:	16.8 microns
25	radius	:	14.8 microns
	root angle	:	90 degree
	pitch	:	50 microns
	chord width/pitch	:	33.6%

"Gain" refers to the ratio of the brightness of a backlit display equipped with a brightness enhancing film to the brightness of the display in the absence of the film. The "viewing angle" is the angle at which the on-axis brightness drops by 50%. It is measured in both the horizontal plane (i.e., in a plane parallel to the long axis of the prisms forming one surface of the brightness enhancement film) and the vertical plane (i.e., in a plane perpendicular to the long axis of the prisms).

The gain and viewing angles of the film were measured using an Eldim EZ Contrast Conoscopic Measurement Device (available from Eldim Co. of Caen, France) equipped with a Sharp STN backlight model C12P (available from Sharp Co. of Tokyo, Japan) as the backlighting source. The Conoscopic Measurement Device provides a plot of gain versus viewing angle in both the vertical and horizontal planes. The maximum slope of the curve provides a measure of the "softness" of the brightness cut-off, with smaller slopes being desirable. The results are as follows:

Gain	:	1.30
View Angle (Vertical)	:	37.0E
View Angle (Horizontal)	:	51.9E
Max. Slope (Vertical)	:	0.0576 gain/E
Max. Slope (Horizontal)	:	0.0612 gain/E

20

Example 2

A film was prepared according to Example 1 except that the film was a Tekra Marnot™ XL Matte Melinex^R 20 GU film. Following cure, the film was separated from the master to yield a product having a surface characterized as follows:

chord width	:	10.4 microns
radius	:	10.5 microns

root angle : 90 degree
pitch : 50 microns
chord width/pitch : 20.8%

5 The gain, viewing angles, and maximum slope of the gain versus viewing angle plot were determined as described above. The results are as follows:

Gain	:	1.28
View Angle (Vertical)	:	37.4E
View Angle (Horizontal)	:	53.2E
10 Max. Slope (Vertical)	:	0.0495 gain/E
Max. Slope (Horizontal)	:	0.0584 gain/E

Other embodiments are within the following claims.

For example, the article may feature a base in which the blunted or
15 rounded peaks are integrally formed with the base and the matte surface is provided in the form of a separate resin layer on the base. Alternatively, the matte surface may be integrally formed with the base and the peak-bearing surface provided in the form of a resin layer.

The brightness enhancement article may be combined with one or more
20 additional brightness enhancement articles. Such additional articles may be the same or different from the original article. For example, the article may be combined with a second brightness enhancement article having prisms terminating in pointed peaks, rather than a rounded or blunt peaks.

What is claimed is:

1. A brightness enhancement article comprising:

(a) a transparent, flexible substrate;

5 (b) a first major surface comprising an array of linear prisms having blunted or rounded peaks characterized by a chord width, cross-sectional pitch width, and radius of curvature in which the chord width is equal to about 20-40% of the cross-sectional pitch width and the radius of curvature is equal to about 20-50% of the cross-sectional pitch width; and

10 (c) a second major surface characterized by a plurality of light scattering protrusions,

said article having a haze value between about 20-60% and a transmission value no greater than about 94% when measured under conditions in which said first surface has a substantially planar topography.

15

2. A brightness enhancement article according to claim 1 wherein said prisms are characterized by a root angle ranging from about 70E to about 110E

20 3. A brightness enhancement article according to claim 1 wherein said prisms are characterized by a root angle ranging from about 85E to about 95E.

4. A brightness enhancement article according to claim 1 wherein said prisms are characterized by a root angle of about 90E.

25

5. A brightness enhancement article according to claim 1 wherein said second major surface is integral with said substrate.

6. A brightness enhancement article according to claim 1 wherein

said second major surface is defined by a layer comprising a resin provided on said substrate.

7. A brightness enhancement article according to claim 6 wherein
5 said light scattering protrusions comprise particles dispersed in said resin.

8. A brightness enhancement article according to claim 6 wherein
said light scattering protrusions are integral with said resin layer.

10 9. A brightness enhancement article according to claim 1 wherein
said first major surface is integral with said substrate.

10. A brightness enhancement article according to claim 1 wherein
said first major surface is defined by a layer comprising a resin provided with said
15 prisms.

11. A brightness enhancement article comprising:
(a) a transparent, flexible substrate;
(b) a first major surface defined by a layer comprising a resin provided
20 on said substrate,
said first major surface comprising an array of prisms having blunted or
rounded peaks characterized by a chord width, cross-sectional pitch width, and
radius of curvature in which the chord width is equal to about 20-40% of the cross-
sectional pitch width and the radius of curvature is equal to about 20-50% of the
25 cross-sectional pitch width; and
(c) a second major surface defined by a layer comprising a resin
provided on said substrate,
said second major surface comprising a plurality of light scattering
protrusions,

said article having a haze value between about 20-60% and a transmission value no greater than about 94% when measured under conditions in which said first surface has a substantially planar topography.

5 12. A brightness enhancement article according to claim 11 wherein said prisms are characterized by a root angle ranging from about 70E to about 110E.

10 13. A brightness enhancement article according to claim 11 wherein said prisms are characterized by a root angle ranging from about 85E to about 95E.

 14. A brightness enhancement article according to claim 11 wherein said prisms are characterized by a root angle of about 90E.

15 15. A method of enhancing the brightness of a uniform, diffusely-emitting, lighting device having a light-emitting surface,

 said method comprising placing a brightness enhancement article substantially parallel to said light-emitting surface,

 said article comprising:

20 (a) a transparent, flexible substrate;

 (b) a first major surface comprising an array of prisms having blunted or rounded peaks,

 said peaks being characterized by a chord width, cross-sectional pitch width, and radius of curvature in which the chord width is equal to about 20-40% of the cross-sectional pitch width and the radius of curvature is equal to about 20-50% of the cross-sectional pitch width; and

25 (c) a second major surface characterized by a plurality of light scattering protrusions,

 said article having a haze value between about 20-60% and a

transmission value no greater than about 94% when measured under conditions in which said first surface has a substantially planar topography.

16. A method according to claim 15 comprising placing said
5 brightness enhancement article substantially parallel to the light-emitting surface of a back-lit display device.

17. A method according to claim 15 comprising placing said
brightness enhancement article substantially parallel to the light-emitting surface of
10 a back-lit liquid crystal display device.

18. A device comprising:

(a) a uniform, diffusely-emitting, lighting device having a light-emitting surface; and

15 (b) a brightness enhancement article placed substantially parallel to said light-emitting surface,

said brightness enhancement article comprising:

(i) a transparent, flexible substrate;

(ii) a first major surface comprising an array of prisms having
20 blunted or rounded peaks characterized by a chord width, cross-sectional pitch width, and radius of curvature in which the chord width is equal to about 20-40% of the cross-sectional pitch width and the radius of curvature is equal to about 20-50% of the cross-sectional pitch width; and

(iii) a second major surface characterized by a plurality of light
25 scattering protrusions,

said article having a haze value between about 20-60% and a transmission value no greater than about 94% when measured under conditions in which said first surface has a substantially planar topography.

19. A device according to claim 18 wherein said lighting device is
in the form of a back-lit display device.
20. A device according to claim 18 wherein said lighting device is
5 in the form of a back-lit liquid crystal display device.

1/1




Fig. 1




Fig. 2

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 98/09278

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 G02B5/02 G02B5/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 G02B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	PATENT ABSTRACTS OF JAPAN vol. 097, no. 009, 30 September 1997 & JP 09 113902 A (DAINIPPON PRINTING CO LTD), 2 May 1997 see abstract	1, 11, 15, 18
A	EP 0 556 606 A (SEIKISUI CHEMICAL CO LTD) 25 August 1993 see page 9, line 11 - line 23; figures 15, 16, 25 see page 4, line 9 - page 7, line 34	1, 11, 15, 18
A	EP 0 770 902 A (TOPPAN PRINTING CO LTD) 2 May 1997 see abstract; claim 1; figure 4	1, 11, 15, 18

	---/---	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

18 August 1998

Date of mailing of the international search report

26/08/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Hervé, D

INTERNATIONAL SEARCH REPORT

Int: lional Application No

PCT/US 98/09278

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication where appropriate, of the relevant passages	Relevant to claim No.
A	JP 01 161 328 A (DAINIPPON PRINTING CO LTD) 26 June 1989 see abstract ----	1
A	DE 42 32 977 A (KEIWA SHOKO K K) 15 April 1993 see column 2, line 64 - column 3, line 59; claim 1; figure 1 -----	5-9

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/09278

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0556606 A	25-08-1993	JP 2723414 B	09-03-1998
		JP 5203950 A	13-08-1993
		JP 2705868 B	28-01-1998
		JP 5313004 A	26-11-1993
		JP 6043310 A	18-02-1994
		CA 2088113 A	28-07-1993
		DE 69317133 D	09-04-1998
		US 5394255 A	28-02-1995
		US 5552907 A	03-09-1996
		US 5764315 A	09-06-1998
EP 0770902 A	02-05-1997	JP 9120101 A	06-05-1997
		JP 9269546 A	14-10-1997
JP 01161328 A	26-06-1989	NONE	
DE 4232977 A	15-04-1993	KR 9615775 B	21-11-1996
		US 5706134 A	06-01-1998